

**Review**

## **Future direction of Au agromining on how to solve artisanal and small scale gold mining problems**

**Abd Mujahid Hamdan<sup>1\*</sup>, Rizna Rahmi<sup>1</sup>, Abd Hafidz<sup>2</sup>, Rispalman<sup>3</sup>**

<sup>1</sup> Environmental Engineering Department, Faculty of Science and Technology, State Islamic University of Ar-Raniry Banda Aceh, Indonesia

<sup>2</sup> Department of Geophysical Engineering, Faculty of Mining and Petroleum Engineering, Institut Teknologi Bandung, Indonesia

<sup>3</sup> Department of Law, Faculty of Law and Syariah, State Islamic University of Ar-Raniry Banda Aceh, Indonesia

\*corresponding author: abd.mujahid.hamdan@gmail.com

---

### **Abstract**

#### *Article history:*

Received 19 May 2021

Accepted 7 June 2021

Published 1 July 2021

#### *Keywords:*

Au agromining  
hyperaccumulators  
ASGM  
Indonesia

Indonesia is one of the countries with the largest Au deposited. Gold mining has been the backbone of Indonesia's economy. However, Indonesia also faces huge problems of Artisanal and Small Scale Gold Mining (ASGM) in a number of areas of Indonesia. A number of problems follow this Au mining method, including environmental, social and economic problems. Green innovation and technologies are needed to solve the problems. To date, Au agromining has been considered as a technology that can solve the numerical problems of Au conventional mining in the sector mentioned before. Gold agromining also has been proposed as a solution for the ASGM problem in Indonesia. However, until now, there have been no reports on the use of Au agromining technology in Indonesia. In fact, agromining research has been very advanced and is considered very prospective. This paper outlines the potentials of Au agromining to be implemented in Indonesia to overcome the social and environmental problems of ASGM.

---

**To cite this article:** Hamdan, A.M., Rahmi, R., Hafidz, A. and Rispalman. 2021. Future direction of Au agromining on how to solve artisanal and small scale gold mining problems. *Journal of Degraded and Mining Lands Management* 8(4): 2971-2984, doi: 10.15243/jdmlm.2021.084.2971.

---

### **Introduction**

Indonesia is one of the regions crossed by the Cenozoic magmatic arc, which is the boundary of the Eurasian and Indo-Australian plates. This fact cause Indonesia has had a number of Au deposits (Syafrizal et al., 2017; Thomsen, 2017). Gold mining on Indonesia had begun since the 19<sup>th</sup> century (Van der Eng, 2014; Leeuwen et al., 2014). Gold mining is spread across several islands including Papua, Sumbawa, East Kalimantan, Sumatra and Central Kalimantan (Leeuwen et al., 2014). Indonesia has very large Au reserves. In 2016, Indonesia was estimated to produce 4% of Au global and has produced 91 tons of Au. Proved Au reserve of Indonesia for placer gold is 15.5 tons, and primary gold is 2,626.7 tons (Performance Report of the Directorate General of Mineral and Coal, 2016). The mining

sector, including Au mining, accounts for 6-12% of the gross domestic product (GDP) of Indonesia. This has made the Au mining sector one of the backbone of the Indonesian economy (Soelistijo et al., 2015; Spiegel et al., 2018). Until 2010, more than one million workers were involved in the mining sector of Indonesia. Indonesia is currently listed as one of the largest producers and exporters of Au (Topstad and Karlsen, 2015). Mining operations in Indonesia have encouraged employment opportunities, construction of infrastructure and development of remote areas. However, in the past decade, activities of artisanal small-scale gold mining (ASGM) are serious problems for Indonesia. In this method, the technique of Au extraction uses mercury (Hg) and/or cyanide (CN). Mercury has a high level of toxicity. Therefore, activities of ASGM are considered to threaten public

health and environmental sustainability (Arifin et al., 2015). There is a total of 100-500 tons of Hg per year are estimated to be used for activities ASGM in Indonesia. That number causes Indonesia has been reported as the third-largest country that releases Hg to the environment in the two last decades after China and India (Spiegel et al., 2018). Activities of ASGM in Indonesia has also raised severe problems in other aspects, including politics, security, law, human rights, social and economic (Hentschel et al., 2003; Kumah, 2006; Bernhoft, 2012; Veiga et al., 2014; Macdonald et al., 2014; Northey et al., 2014; Calvo et al., 2016; Spiegel et al., 2018; Mutsvanga et al., 2018; Tayebi-Khorami et al., 2019; Levinson and Dimitrakopoulos, 2019).

The alternative technology and new innovation are expected to replace the ASGM method (Kumah, 2006; Wilson-Corral et al., 2012; Van der Ent et al., 2015; Basu et al., 2015). Those technologies must be effective, be economical and be environmentally friendly. To date, alternative technology that has these advantages is Au phytomining (Van der Ent et al., 2013; Krisnayanti et al., 2016). Au phytomining and/or Au agromining are the use of plants for extracting metals by three stages, including (i) cultivating of plants, (ii) extraction of Au into plant tissue (shoot), and (iii) processing of biomass to separate Au targeted. The term agromining refers to unproductive lands for food crops due to the land contains toxic metals (Krisnayanti and Anderson, 2014; Van der Ent et al., 2015; Kidd et al., 2018). Krisnayanti and Anderson (2014) and Krisnayanti et al. (2016) have proposed Au phytomining for the management of ASGM's tailing amalgamation. Subsequently, Krisnayanti et al. (2016) have shown that this technology can be carried out directly by the ASGM community in West Nusa Tenggara, Indonesia. Several laboratory studies and field trials have shown that this technology is more environmentally friendly and economical than the conventional method, especially on tailing waste management (Anderson et al., 2005; Sheoran et al., 2009; Wilson-Corral et al., 2012). Gold agromining is considered potential as a more integrated solution in social, economic and public health aspects to overcome the problem of ASGM's tailing management in Indonesia (Krisnayanti et al., 2016). However, there are some gaps in research for implementing this concept, especially for ASGM management. This paper describes those gaps and outlines the future direction of Au phytomining as a substitute for ASGM. The discussion focuses on Indonesia's case, but this projection can be widely applied.

### ASGM in Indonesia

Artisanal and Small Scale Gold Mining (ASGM) is a term for informal Au mining by traditional technologies. This method can be carrying out by individual, groups or families (Krisnayanti et al., 2012;

Krisnayanti, 2018; Puluhalawa and Harun, 2019). The stages of ASGM consist of amalgamation, tailings processing and gold recovery. These processes emit Hg into the environment. Besides Hg, some ASGM in Indonesia also uses cyanide (CN) (McDonald et al., 2014). In the process, ore processing is carried out by grinding using a roller. Then, Hg is mixed into ore to get Au-Hg amalgam. Amalgamation can be repeated several times until the Au in the ore is considered to be no longer extractable. The process results in tailings being dumped into the environment. To obtain the Au, the Hg in amalgamation is evaporated by heating. Thus, Hg can pollute the environment through (1) dissolved mine waste (Hg leached tailings) which then transported into the hydrological system, and (2) Hg vapour emissions into the atmosphere. Because of this process, ASGM has become the largest source of Hg pollution in the world (Azis, 2014; Macdonald et al., 2014; Esdaile et al., 2018; Puluhalawa and Harun, 2019).

Activities of ASGM have risks to nature and human. The miners of ASGM are nomadic communities. They build temporary shelters in sites of ASGM. The shelter is inadequate because it does not have a good sanitation system. In North Gorontalo, Hg had been found in the community's hair tissue higher than threshold levels. Because of that, many miners and communities have got health problem of the nervous system (Arifin et al., 2015 and Macháček, 2019). Basically, the communities and miners have known the risks of ASGM. However, economic motivation is more dominant than awareness of health risks that be faced (Basri et al., 2017; Trimiska et al., 2018).

Activities of ASGM have changed the function of agricultural land, changed topography, and disrupt the hydrological system. In Lombok and Sumbawa, activities of ASGM are carrying out around rice farming areas. Thus, the farming lands in that area have been contaminated by Hg on a very higher level than the threshold level. Besides that, several ex ASGM lands have been converted to cropland without remediation of Hg and CN that be released from amalgamation and cyanidation. The concentration of Hg within the soil of that land reaches 8,364 ppm (Krisnayanti, 2018).

ASGM has also caused many hydrometeorological disasters, including flood and landslide, then cause losses and casualties (Damanik, 2019; Plasmanto, 2019). One of the cases, in 2020, flood and landslide due to ASGM have occurred at Bogor, then because of this disaster, 21,742 people had to be displaced (Wisuda, 2020). However, Indonesia is one of the largest users of ASGM. The distribution points of ASGM in Indonesia is shown in Figure 1. The miners of ASGM are nomadic communities. They build temporary shelters in sites of ASGM. The shelters are inadequate because they do not have a good sanitation system. In 2010, more than 850 ASGM cites were found in 27 provinces.




Figure 1. Distribution points of ASGM in Indonesia.

UNEP estimates that there are 300,000 miners of ASGM in Indonesia (Balifokus, 2013; 2015; UNEP Final Report, 2014). This problem cannot be viewed only from the perspective of public health. ASGM in Indonesia is a complex problem that deals with social, economic and political issues. ASGM has triggered social conflict in the sites. The conflicts consist of land grabbings, violence among communities and miners, and cases of gold grabbing (Al Zuhri, 2015). These conflicts due to lack of law enforcement, economic pressure of miners and/or communities and absence of clear and stick regulation for ASGM. Law enforcement is an effort for social control and also social engineering. Weak enforcement of regulations due to the government is faced with dilemma problems. ASGM has been considered as a source of livelihood who have no skills and skills. On the other hand, ASGM is considered as a more equitable approach to natural resources exploitation and provide direct benefits for society. Controlling ASGM is very difficult because most ASGM in Indonesia is illegal. Most ASGM in Indonesia is in rural areas where the condition of the people is still below the poverty line (Hentschel et al., 2003; Manus, 2005; Male et al., 2013; Krisnayanti et al., 2016; Puluhulawa and Harun, 2019).

The tending of communities to be ASGM miners is driven by several factors, including lack of employment, low education level of miners, community perceptions, and the low price of Hg. Most miners are people who live along the poverty line, and they do not have a good level of education. The low level of education cause miners to not have sufficient knowledge of public health and environmental sustainability. In addition, community perceptions in a number of locations assume that the job as an ASGM miner has been inherited from their ancestors. The

other factor is the availability of cheap Hg. Indonesia has local mercury production, which has driven the price of mercury affordable for ASGM (Obiri et al., 2016; Redi, 2016; Spiegel et al., 2018).

However, ASGM has considered overcoming several economic problems. ASGM is an attractive alternative livelihood for rural workers because it has good potential to improve the wealth of a community. In general, ASGM has increased income and the availability of employment opportunities (Krisnayanti, 2018; Owusu et al., 2019). Therefore, ASGM should be regulated in such a way that regulations and policies are oriented towards environmental sustainability and public health. The Indonesian government has committed to regulating ASGM activities by considering all environmental risks that may arise, including by regulating the use of Hg. Several approaches have also been proposed to overcome Hg emissions from ASGM activities, including by breaking the mercury marketing chain (McGrew, 2016; Spiegel et al., 2018; Puluhulawa and Harun, 2019). In order to solve job opportunity and environmental problems simultaneously, green technology and new approaches for the community are needed.

### Gold Agromining Technology

Since the ability of plants to extract the metals in a large amount into their tissues, the concept of phytoextraction has been developed to be more advanced, such as phytomining and phytoremediation. Phytoremediation is remediating contaminated land by using plants. Meanwhile, phytomining is minerals exploitation by also using plants. Phytomining has been considered to be prospective for future mining technology. This approach is environmentally friendly and inexpensive. The approach also can be used to be

an alternative to replace conventional methods on certain land characteristics. The characteristics of that lands including low grade and uneconomic land that is mined by conventional methods and where is not accessible by heavy equipment. The term for phytoextraction on unproductive agricultural areas due to high metal content is agromining (Bani et al., 2007; Verbruggen et al., 2009; Callahan et al., 2012; Fernando et al., 2013; Orłowska et al., 2013; Boas et al., 2014; Van der Ent et al., 2015; Kidd et al., 2018). However, the term can be expanded for mining on land using crop technology and to be used by farmers or communities.

The term phytomining is used based on metal targeted. Gold phytomining is phytomining for Au as metal targeted. To date, Au phytomining was proposed as a method of processing tailings from the remaining gold metallurgical activities. The tailing can be originated from the company scale or ASGM scale (Wilson-Corral et al., 2012; Krisnayanti et al., 2016). The idea based on the fact that Au can be found within mine tailings and mine wastes at a high content level. The recycling capital needed is too high compared to the benefits obtained (Anderson et al., 1998). In addition, Au phytomining has also considered being economical to exploit a low grade auriferous. Low grades of auriferous can be found on several characteristics of land, including (i) lands that are not economical due to the reduction of reserves, (ii) lands with auriferous that are not economical to exploit, and (iii) waste mining lands that are not economical to process (Wilson-Corral et al., 2012; Kivinen, 2017). Anderson (2005) argued that the use of the term "mining" in explaining the ability of plants to extract metals from the soils is a misconception. This method is not considered a competitor for conventional mining (Anderson et al., 1998). However, the term agromining in some literature is still relevant because this technology can be a substitute for conventional methods on lands with certain characteristics (Van der Ent et al., 2013; Van der Ent et al., 2015; Kavanagh et al., 2018).

### **Gold hyperaccumulator**

The plants that to be used in agromining are called hyperaccumulators or hyperaccumulating plants. These plants can absorb heavy metals in high concentrations into the tissues. In biological science, heavy metals refer to metals or metalloids needed by organisms but in very low concentrations. The metals and metalloids then become toxic if they accumulated to the tissue in higher concentrations threshold are they have (Rascio and Navari-Izzo, 2011). However, a hyperaccumulator can absorb metals on a higher level of toxic level threshold (Sheoran et al., 2013; Sobczyk et al., 2017). The kind of hyperaccumulator can be grouped by the metal they accumulate. So, hyperaccumulating plants for Au are called Au hyperaccumulators. Gold hyperaccumulators are all

plants that can absorb Au higher than 1 µg/g of dry biomass (Anderson et al., 2003).

In the beginning, the presence of Au in plant tissues was suspected to be an indicator of Au exploration (Brooks 1982; Girling and Peterson, 1980). Some plants have been discovered to accumulate Au, such as *Pseudotsuga menziesii*, *Pinus banksiana*, *Picea mariana*, *Hordeum vulgare* and *Phacelia sericea* (Shacklette et al., 1970; Bali et al., 2009). The mechanism of Au accumulation into the foliage is still not fully understood. In general, Au into the tissue consists of 1) solubilization of Au of the soil matrix, 2) gold uptake into the root of hyperaccumulator, 3) transport to the shoots, detoxification and sequestration in the tissues of hyperaccumulator (Sheoran et al., 2013). Gold in *Brassica juncea* is accumulated in the form of biogenic particles in the carbon matrix (Anderson et al., 2013). The mechanism of Au accumulation has not been deep as understanding for mechanisms of Ni or Zn accumulation (Reeves and Adigüdzsel, 2008; Deng et al., 2018).

Furthermore, the use of these plants has been developed as mining technology, as we described before. To date, *Brassica juncea* and some crops such as carrots, onions, red yams and turnip have been used in simulations of the implementation of gold phytomining in the field (Msuya et al., 2000; Anderson et al., 2005). In the practice of Au agromining, the use of local species is a key factor in the success of Au agromining. This is because of the adaptation ability of local species to the soil and climate conditions. In addition, the use of non-native species has the potential to disrupt local biodiversity (Prasad and Freitas, 2003; Ghosh and Singh, 2005; Prasetya et al., 2010).

The processes of Au accumulation by plants are affected by both biological and physical factors. The factors are including bioavailability, rhizosphere, plant interactions with microbes, root exudation and plant transpiration (Gove et al., 2002; Gardea-Torresdey et al., 2005; Wilson-Corral et al., 2011; Wilson-Corral et al., 2013; Reith et al., 2013). Although transpiration is affecting gold transport in plants, in some species, transpiration factors do not look significant (Girling and Peterson, 1980). The ability of the hyperaccumulator to absorb Au is also determined by the solubility of gold in the soil.

In natural conditions, Au has a low solubility. Therefore, the addition of injection fluid is a decisive step in Au agromining (Anderson et al., 1998; Gardea-Torresdey et al., 2005; Wilson-Corral et al., 2013; Reith et al., 2013). To date, a plant that naturally absorbs Au to the tissues in high-level concentration has not been found. The accumulation of Au needs fluid injection uptake Au from ore to the tissue. Gold hyperaccumulator is unlike Ni hyperaccumulators that can accumulate Ni naturally without fluid injection. However, a certain chemical can stimulate Ni absorption.

Table 1. The list of Au hyperaccumulators, the concentration of Au in the foliage, and chemical induction list.

Species	Au (µg/g)	Author	Chemical Induction
<i>Brassica juncea</i>	0.37-57.2	Anderson et al., 1998; Anderson et al., 1999; Lamb et al., 2001	NaSCN, KBr, KCN, KI, (NH <sub>4</sub> ) <sub>2</sub> S <sub>2</sub> O <sub>3</sub> .
Chicory	0.07 -1.19	Anderson et al., 1998; Anderson et al., 1999; Lamb et al., 2001	NaSCN, KBr, KCN, KI
<i>Impatiens sp</i>	3.09	Anderson et al., 1998; Anderson et al., 1999	-
<i>Arrhenatherum elatius</i>	0.07 - 1.43	Anderson et al., 1998; Anderson et al., 1999	-
<i>Daucus carota</i> L		Msuya et al., 2000	thiocyanate; thiosulfate
<i>Allium cepa</i> L.		Msuya et al., 2000	thiocyanate; thiosulfate
<i>Beta vulgaris</i> L		Msuya et al., 2000	thiocyanate; thiosulfate
<i>Raphanus sativus</i>		Msuya et al., 2000	thiocyanate; thiosulfate
Oriental radish		Msuya et al., 2000	thiocyanate; thiosulfate
Tobacco	1,2	Krisnayanti et al., 2016	NaCN
<i>Paspalum conjugatum</i>	601.9	Handayanto et al., 2014	ammonium thiosulfate
<i>Trifolium repens</i>	27,000	Piccinin et al., 2007	ammonium thiosulfate
<i>Helianthus annuus</i>	119,000-141,000	Wilson-Corral et al., 2012	NaCN
<i>Chilopsis linearis</i>	18,000	Gardea-Torresdey et al., 2005	NH <sub>4</sub> SCN
<i>Sorghum halepense</i>	31,000	Rodriguez-Lopez et al., 2009	NaCN
<i>Trifolium repens</i> L. cv. Prestige	> 27,000	Piccinin et al., 2007	NaCN
<i>Medicago sativa</i> L. (alfalfa)	40,900	Gardea-Torresdey et al., 1999	thiourea
<i>Kalanchoe serrata</i>	21,700	Gardea-Torresdey et al., 1999	thiosulphate
<i>Zea mays</i> L	600	Anderson et al., 2005	<i>Zea mays</i> L
<i>Barceya coddii</i>	97,000	Lamb et al., 2001	NaSCN, KCN

### Gold agromining cultivation techniques

Cultivation of agromining has two main aspects. These are the selection of species and cultivation methods. The candidate of species should be resistant to conditions of temperature, water stress, salinity and pH. Therefore, the plants suggested being used are endemic or native species. In addition, an effective species has a short duration of growing and have a large amount of biomass (Anderson et al., 2005; Sheoran et al., 2013).

In practice, cultivation aspects consisted of characterization of soils, drainage systems, planting systems, injection fluid selection and fertilization (Keeling et al., 2003; Anderson et al., 2005; Hunt et al., 2014). The effect of soil moisture has been investigated on the amount of biomass production. This parameter is linear to biomass production (Wilson-Corral et al., 2012; Nkrumah et al., 2018). For cultivating ore tailing, Swaroop et al. (2013) have successfully used gold ore tailing as media for *Brassica oleracea* and *Brassica oleracea* var. Capitata. This result indicates that fertilization must consider the micronutrient content of ore. The minerals content of the soil will affect the pH value of soils. Then, the value of pH greatly affects the ability of plants to accumulate metals (Gramss et al., 2004). For Au extraction, the optimum pH is 8.9-9.5 (Wilson-Corral

et al., 2012). But, Au can only be dissolved and then form complexes in low pH soil conditions. Meanwhile, Au is insoluble in the soil. This fact has made Au agromining has bigger limitations than Ni agromining technology (Shooran et al., 2013; Ali et al., 2017). So, on Au extraction, a chemical fluid is needed to inject Au into the foliage, but the addition of fluid induction has the potential to affect the soil characteristic, including pH, microbial life and potentially cause destructive of soil quality (Lamb et al., 2001; Grčman et al., 2001). That is a challenge for cultivating Au agromining, because biomass production factor, accumulation of Au factors and environment management factors are important aspects to be considered.

Therefore, the selection of chelation agents is a crucial factor in cultivation (Wilson-Corral et al., 2012). A number of chemical liquids have been considered to be the potential induction fluids, as shown in Table 1 (Gardea-Torresdey et al., 2005; Wilson-Corral et al., 2012). However, the safety control for the environment has to get more attention because some fluids injection have a high level of toxicity, such as potassium cyanide (MacDonald, 2015; Ali et al., 2017; Jaszczczak et al., 2017).

The transpiration rate is considered to be one of the success factors of phytoextraction (Leitenmaier and Küpper, 2013). However, hyperaccumulator

transpiration is known to be influenced by genotype and/or evolutionary factors. Ecotype factors include morphological characteristics, width and thickness of leaves and number of stomata. Meanwhile, climate conditions are thought to be the cause of genetic evolution in order to adapt to local climate (Lu et al., 2008; Wan et al., 2015).

### **Biomass processing**

Several methods have been proposed and implemented in the processing of hyperaccumulator biomass, such as composting, combustion, gasification and hydrometallurgy (Mohanty, 2016; Simonnot et al., 2016). On processing of Ni biomass, since Lamb et al. (2001) found that leaching by using HCl is non-green and expensive, further ideas had been investigated. Based on an experiment, the processing of *A. murale*'s biomass by leaching indicates 0.5 M H<sub>2</sub>SO<sub>4</sub> at 90°C could extract 97.0 ± 6.8% of Ni. According to Barbaroux (2009), hydrometallurgy is more economical than the combustion method. However, using hard acid is considered a non-green method and trigger a new environmental problem. Both the cost and sustainability aspects are the main consideration to find the method of biomass processing. According to Krsnayanti et al. (2016), the hydrometallurgy approach for Au biomass processing is not economically promising. Furthermore, Krisnayanti et al. (2016) proposed processing tobacco biomass with ashing and smelting using borax. This method has been simplified to save reagents and decrease the costs (Wood et al., 2006; Losfeld et al. 2012; Simonnot et al., 2016; Chaney and Baklanov, 2017).

### **Implementation Au agromining to Substitute ASGM**

Opportunities for implementation of Au agromining in Indonesia are supported by several factors, including: (1) Indonesia has high biodiversity; thus, the opportunities to find the Au hyperaccumulators are enormous; (2) Indonesia has a tropical climate, so the hydrological system, soil moisture and plant transpiration rates support the cultivation of the Au hyperaccumulators; and (3) The abundance of auriferous deposits in Indonesia so Au mining activities in Indonesia have the prospect to continue to be developed. On the other hand, the Indonesian government provide a continuous irrigation system to reach all areas of national agriculture.

A field for Au agromining should be designed by several considerations, including environmental safety and effectiveness of Au agromining processes. The chemical injection used is the major issue of environmental safety. Therefore, according to this issue, the land's design must follow specific conditions, including (i) the land system does not emit heavy metal to the environment such as surface water, groundwater, soil and air, and (ii) the land has a good drainage system that can localize the induction fluid

used (Wilson-Corral et al., 2012). For this consideration, the aquaculture lining system is the best candidate to be adopted in the agromining system (<https://www.climaxindia.com/aquaculture.html>). This system has been used in various fields of agriculture and is considered to be able to increase the productivity of agricultural products.

Cultivation of plants can be carried out either ex-situ or in-situ. For ex-situ cultivating, the stages consist of (i) ore crushing, (ii) land preparation (iii) installation of liner layers (iv) ore transportation (v) land management (vi) planting (vii) maintenance and (viii) harvesting. But for in-situ, the stages consist of the same steps as the ex-situ except for the ore transportation stage. The choice of whether to be implemented ex-situ or in-situ depends on the characteristics of the land, the availability of land, the source of water for cultivation and environmental factors. According to Krisnayanti et al. (2016), agromining is better if it is done on flat land because the drainage system will be more effective and efficient to be designed on this characteristic land.

In addition to technology development, another challenge is the acceptance of the community to this technology. Krisnayanti et al. (2016) have conducted an experiment of Au agromining for amalgamation tailing of ASGM management in Indonesia. According to Krisnayanti et al. (2016), the ASGM community was very sceptical to Au agromining technology. This is because the community considers that ASGM more has economic benefits instantly, in contrast to agromining, which takes 3 to 4 months for harvesting. In addition, crop cultivation has the risks of crop failure and additional costs that are not required by conventional methods. Therefore, the agromining implementation as a substitute for ASGM requires a socialization approach, strengthening commitment and reward (Goodman and Griffith, 1991). The approaches are also based on political, regulatory, social and economic policies.

To date, tobacco, maize, sunflower and cassava have been tested as local plants that can be used as accumulators for Au Agromining (Krisnayanti and Anderson, 2014; Krisnayanti et al., 2016). Based on the number of species that have been tested, local Indonesian species for Au extraction have not been identified massively. Currently, Au hyperaccumulators are also still much less when compared with the number of Ni hyperaccumulators that have been identified (Reeves et al., 2017; Sobczyk et al., 2017). However, the discovery of Indonesian native or endemic species for Au agromining has enormous opportunities. The geographical conditions make Indonesia the centre of world biodiversity. 28,000 plant species are estimated to grow in the Indonesian territory. This number makes Indonesia a megadiversity country (Astirin, 2000; Sastrapradja, 2005; Rintelen et al., 2017). There are two basic choices for species to be cultivated, namely the ability of plants to survive in the environment and economic

factors. The species chosen should be species that are already local varieties commonly commercialized among farmers. This is because farmers already expert cultivation techniques well compared to non-local species or which are not local varieties that are often cultivated (Krisnayanti et al., 2016).

### Gold Agromining as Solution for Problems of ASGM

Gold agromining has been proposed as an approach for tailing management and beneficial purposes simultaneously (Sheroan et al., 2013). Based on the aspect of Au agromining as described before, this approach has the potential to be used for substitute ASGM. That is because the main technology is adopted from agriculture technology that is very familiar to the community, especially in agrarian countries. There is some addition and difference technique, but the framework is not different. Therefore, this technology has the prospect to be applied neither individually nor group farmers.

Gold agromining as a candidate of substitute of ASGM must occupy sustainability principles that have been proposed by The International Council on Mining and Metals (ICMM). These principles have been proposed for waste mining management. According to Tayebi-Khorami et al. (2019), those principles can be summarized in five key aspects, including social dimensions, geoenvironmental aspects, geometallurgy specifications, economic drivers, and legal implications into five integrated areas. The principles are hoped can overcome the problem comprehensively to some various aspects and perspectives (Basu et al., 2015). However, the principles and key aspects can be adopted to assess Au agromining as a substitute for ASGM.

#### Economic aspect

Mining has to be a driver for a circular economy (Tayebi-Khorami et al., 2016). In addition, the benefit distribution on Au deposit also one of the issues that can trigger a social problem. In Indonesia, as a developing country, sharing of economic values of Au mining that is carried out by corporation has been a national issue. A large number of ASGM on-site with Au abundance is evidence that the natural resources do not have an economic impact on society directly. Gold exploitation that has been carried out by mining company has considered can not have an economic impact directly on society. This is due to conventional mining need a large capital, and it also only can be carried out by conglomeration.

Based on that issue, new technology is needed which can distribute economic values directly to society. Gold agromining will give the new economic impact, including: giving job opportunities, land use optimization, the emergence of biomass processing plants, the emergence of chemicals distributors for Au agromining, the emergence of biomass and its

processing products distributors, and the emergence of new industries that utilize Au agromining results that were not there before. The stages of Au agromining can be grouped on land preparation, cultivating, Au production and Au marketing. Each group has the potential to create a new job opportunity. On land preparation, the new job is surveying service, economic analyst, soils and ore analyst, soil and irrigation preparation. Cultivating for Au phytoextraction is one of the choices for the farmers in utilizing their land. This "agriculture" can be chosen if Au agromining is a higher benefit than the other agriculture commodities. Because of that, the companies of biomass processing will be needed for Au production. So, all of the stages are going to create a circular and distribution economy, as shown in Figure 2.

To analyse the economic feasibility of Au agromining as a substitute for ASGM, the study has to consider several factors including predicted annual costs, irrigation, fertilization, plant protection and harvesting; land costs; biomass and its processing, fluid injection, price of the metal, and the value of alternative land uses. This technology is considered to be economical for the processing of auriferous tailing and rock waste of Au mining (Wilson-Corral et al., 2012). But, to extract Au from amalgamation tailing, this method has no conclusion about the beneficial aspect (Krisnayanti et al., 2016). Wilson-Corral et al. (2012) have estimated the net profit obtained of Au agromining is US \$15,098/ha. The economic benefits based on Au content in biomass assuming 8330 kg/ha of dry biomass (Wilson-Corral et al., 2012) are presented in Figure 2a. The benefit based on the amount of biomass produced assuming Au content in plants is 55 mg/kg (Anderson et al., 2005) is presented in Figure 2b. Meanwhile, by summarizing the mathematical model proposed by Anderson et al. (2005), the correlation between the concentration of Au in biomass and that contained in the soil is  $Y = a \ln(x) + C$ , where  $a$  and  $C$  are constants that depend on the species and the induced fluid used,  $Y$  is Au concentration in biomass and  $x$  is the Au concentration in the soil. Economic benefits based on the Au concentration function in the soil (Anderson et al. 2005) are presented in Figure 2c. Indonesia's per capita income is US \$ 4175 per year, so based on Figure 2a, to get a profit above per capita income, the breaking point is around 4000 kg/ha/year of biomass.

The report of Krisnayanti et al. (2016) indicates that Au-phytomining is still an expensive practical to process ASGM tailing. So, the technique still needs to be developed. Further studies are still required to advance to find a cheap fluid injection, a cheap method of biomass processing, and an efficient method of cultivation for maximum benefit. For these purposes, the studies have been still limited. The differences result from these benefit due to the land, ore characteristics, species and cultivation methods are different for each case.




Figure 2. Simulation of profits based on Wilson-Corral (2012) analysis. a) Profit based on level of Au content in the biomass by the assumption that dry biomass is 8,330 kg/ha. b) Profit bases on the amount of biomass by Au content in the dry weight of 55 mg/kg. c). profit based on the function of Au concentration within the soil (Anderson et al., 2005).

That indicates that the wide practical of Au agromining to substitute for ASGM need massive testing and trial. The testing and trial also have to consider the user's aspect. The capital scale and user model is determined the technique that to be used. For example, traditional farmer and farmer group as the user will have a different approach for practical of this method.

#### Geoenvironmental aspect

Waste management of Au mining is a major issue of geoenvironmental aspect of conventional mining. Gold phytomining has been proposed as a technology for waste management. This approach has been considered as a technology that is more economical to recycle both waste rock and waste tailing of metallurgical processes. The environmental problem of leaching for low-grade waste can be reduced by Au phytomining.

Because the model of Au extraction that used is phytoextraction, Au agromining has a lower environmental issue. Gold agromining does not release waste tailing like ASGM. Although, Au agromining is not free-waste mining. Gold grade of auriferous is going to be decreased and in the end, the ore is not still economical. As a substitute for ASGM, waste auriferous management has to be developed for a sustainable environment.

Au agromining has been gotten a critic for using fluid injection to extract Au from the auriferous. However, if this using compared to conventional recycle tailing, the chemicals used are lower. This issue also has to be got attention for its using for farmer/miner of Au agromining. The technique of land

preparation has to be designed for keeping fluid injection, and the heavy metals have no emission to the environment. For the fluid injection excess, bioremediation has been proposed to overcome the problems. For example, for cyanide, several groups of microorganism have been discovered for biodegradation, including bacteria such as *Klebsiella oxytoca*, *Pseudomonas fluorescens*, fungus such as *Fusarium solani*, *Fusarium oxysporum* and algae such as *Scenedesmus obliquus*.

Simultaneously, Au agromining can be a technique to restore the environmental destruction of mining, both ASGM and conventional mining of a company. The agricultural land can be restored that has been decreasing because of ASGM activities. Land reclamation is expected to restore lost economic resources such as agricultural sectors. Some hyperaccumulating plants are known to have phytoextraction ability to multiple metals. There is a possibility that Au and Hg accumulation occurred simultaneously so that phytoextraction can be multifunctional. In addition to Au exploiting, these plants are also expected to be used in removing Hg from the land. Some species that grow in ex-Au mining field in Indonesia have been considered as potential species for Hg remediation from the soils, including *Paspalum conjugatum* (Muddarisna and Krisnayanti, 2015), *Lindernia crustacea*, *Digitaria radicata* and *Cyperus kyllingia* (Muddarisna et al., 2013).

#### Metallurgical aspect

Metallurgy not only involves mining and metallurgical field but can also be integrated into environmental and



economic aspects. Gold biomass metallurgy is more economical and less environmental impact because biometrics of Au is not complex as conventional ore. Bio-ore needs more low energy, then cheaper than conventional mining. Because of the selective accumulation of metal into the plants, bio-ore has fewer contaminants than conventional ore. In addition, bio-ore also does not contain sulfides. Thus, its processing does not contribute sulfur emissions into the atmosphere. Acid rain can cause serious problems for the environment and human health (Semrau, 1971; Sheoran et al., 2013; Van der Ent et al., 2015; Schrama et al., 2017). Therefore, metallurgical processes of bio-ore are greener than metallurgical processes of conventional ore. Besides that, biomass processing research has the potential to find other products besides pure Au. Nickel biomass processing has been directed for Ni salt products and various other products (Wood et al., 2006; Losfeld et al. 2012; Simonnot et al., 2016; Chaney and Baklanov, 2017).

### Social dimension

Gold mining and its waste management must not trigger a social conflict. A social conflict can occur among traditional miner, illegal companies, government or security forces, and community (Rahim, 2017). The rising of conflicts has resulted from various conflict of interest between stakeholders (Miall et al., 2000). Community resistance to the activities of ASGM is an effort to keep the environmental sustainability from activities of mining. For example, in 2011 shooting occurred to the man due to the existence of mining activity in Mandailing Natal, North Sumatera (Ramadhan et al., 2014). Wahyudi and Slamet (2015) investigated response community who live in sites of ASGM; generally, the

community in sites of mining reject activities of ASGM. Meanwhile, conflicts between miners of ASGM triggered by the grab of land and access to the auriferous site. Besides of advantage on the environmental aspect mentioned before, Au agromining has a lower risk of conflict. Because the activity of Au agromining is like the activity of agriculture; therefore, the use of agricultural land has legality of ownership. Activities of Au agromining have a high potential to occurred share value between communities, such as land leasing. Social conflict also can be reduced due to, as an agrarian country, Indonesia has set regulations of land that will encourage the orderly implementation of Au agromining.

### Legal dimension

The legality of ASGM in Indonesia reaps the pros and cons. Some local governments prohibit ASGM activities by considering the highly destructive environmental impacts. But part of it is permitted because it will bring jobs and community welfare. Because Au Agromining does not emit Hg into the environment and can prosper the community, Au Agromining will not reap the pros and cons of the legal aspects.

### Conclusion

Au phytomining is the future technology to solve the problem of ASGM in Indonesia. The problem aspects that are overcome by Au phytomining Au are shown in Figure 3. However, further research is needed to develop this technology, both in the aspects of cultivation, biomass processing and implementation studies.




Figure 3. Diagram of problem-solving to environmental sustainability issues of ASGM.

## References

- Ali, A., Guo, D., Mahar, A., Ping, W., Wahid, F., Shen, F., Li, R. and Zhang, Z. 2017. Phytoextraction and the economic perspective of phytomining of heavy metals. *Solid Earth Discussions*, doi: 10.5194/se-2017-75.
- Al-Zuhri, A. 2015. Conflict without Permission Gold Mining (Peti) in the District Mountain Village Petapahan Pavement Kuantan Singingi. *JOM FISIP* 2(2): 1-11 (in Indonesian).
- Anderson, C.W.N. 2005. Biogeochemistry of gold: accepted theories and new opportunities. In: Shtangeva, I. (ed.), *Trace and Ultratrace Elements in Plants and Soils*. Advances in Ecological Science 20. WIT Press, Boston, pp. 287e317.
- Anderson, C.W.N., Bhatti, S.M., Gardea-Torresday, J. and Parson, J. 2013. In Vivo effect of copper and silver on synthesis of gold nanoparticles inside living plants. *ACS Sustainable Chemistry & Engineering* 1(6): 640-648. DOI: 10.1021/sc400011s.
- Anderson, C.W.N., Brooks, R.R., Stewart, R.B. and Simcock, R. 1998. Harvesting a crop of gold in plants. *Nature* 395(6702): 553-554. doi:10.1038/26875.
- Anderson, C.W.N., Brooks, R.R., Stewart, R.B. and Simcock, R. 1999. Gold uptake by plants. *Gold Bulletin* 32: 48-52.
- Anderson, C.W.N., Moreno, F. and Meech, J. 2005. A field demonstration of gold phytoextraction technology. *Mineral Engineering* 18(4): 385-392, doi: 10.1016/j.mineng.2004.07.002.
- Anderson, C.W.N., Stewart, R.B., Moreno, F.N., Wreesmann, C.T., GardeaTorresday, J.L., Robinson, B. and Meech, J.A. 2003. Gold phytomining. Novel developments in a plant-based mining system. In: *Gold 2003 Conference. World Gold Council, Vancouver*, pp. 35e45.
- Arifin, Y.I., Sakakibara, M. and Sera, K. 2015. Impacts of artisanal and small-scale gold mining (ASGM) on environment and human health of Gorontalo Utara Regency, Gorontalo Province, Indonesia. *Geosciences* 5: 160-176, DOI:10.3390/geosciences5020160.
- Astirin, O.P. 2000. Problems of biodiversity management in Indonesia. *Biodiversitas* 1(1): 36-40, doi: 10.13057/biodiv/d010106 (in Indonesian).
- Aziz, M. 2014. Model of people's gold mining and environmental management of mining in the village area of paningkaban, Gumelar Subdistrict, Banyumas Regency, Central Java. *Dinamika Rekayasa* 10(1): 20-28 (in Indonesian).
- Bali, R., Siegele, R. and Harris, A.T. 2009. Phytoextraction of Au: Uptake, accumulation and cellular distribution in *Medicago sativa* and *Brassica juncea*. *Chemical Engineering Journal* 156: 286-297.
- Balifokus. 2013. ASGM sites: Poboya and Sekotong in Indonesia, [https://ipen.org/hgmonitoring/pdfs/indonesia\\_mercury\\_report-hair-rev-en.pdf](https://ipen.org/hgmonitoring/pdfs/indonesia_mercury_report-hair-rev-en.pdf).
- Balifokus. 2015. International mercury treaty enabling activities program (IMEAP). <http://www.ipen.org/>.
- Bani, A., Echevarria, G., Sulce, S., Morel, J.L. and Mullai, A. 2007. In-situ phytoextraction of Ni by a native population of *Alyssum murale* on an ultramafic site (Albania). *Plant and Soil* 239: 79-89.
- Barbaroux, R., Meunier, N., Mercier, G., Taillard, V., Morel, J.L., Simonnot, M.O. and Blais, J.F. 2009. Chemical leaching of nickel from the seeds of the metal hyperaccumulator plant *Alyssum murale*. *Hydrometallurgy* 100(1-2): 10-14., doi:10.1016/j.hydromet.2009.09.005.
- Basri, B., Sakakibara, M. and Ratnawati, R. 2017. Economic features of the artisanal and small-scale gold mining industry in Bombana, Southeast Sulawesi, Indonesia. *IOP Conference Series: Earth and Environmental Science* 71(2017) 012016, doi:10.1088/1755-1315/71/1/012016.
- Basri, B., Sakakibara, M. and Sera, K. 2017. Current mercury exposure from artisanal and small-scale gold mining in Bombana, Southeast Sulawesi, Indonesia-future significant health risks. *Toxics* 197(1) doi:10.3390/toxics5010007.
- Basu, A., Phipps, S., Long, R., Essegbey, G. and Basu, N. 2015. Identification of response options to artisanal and small-scale gold mining (ASGM) in Ghana via the Delphi process. *International Journal of Environmental Research and Public Health* 12: 11345-11363; doi:10.3390/ijerph120911345.
- Basu, N., Renne, E.P. and Long, R.N. 2015. An integrated assessment approach to address artisanal and small-scale gold mining in Ghana. *International Journal of Environmental Research and Public Health* 12: 11683-11698; doi:10.3390/ijerph120911683.
- Bernhoft, R.A. 2012. Mercury toxicity and treatment; a review of the literature. *Journal of Environmental and Public Health*, Volume 2012, Article ID 460508, doi: 10.1155/2012/460508.
- Boas, L.V., Goncalves, S.C., Portugal, A., Freitas, H. and Goncalves, M.T. 2014. A Ni hyperaccumulator and a congeneric non-accumulator reveal equally effective defenses against herbivory. *Science of the Total Environment* 466-467: 11-15.
- Brooks, R.R. 1982. Biological methods of prospecting gold, *Journal of Geochemical Exploration* 17: 109-122.
- Callahan, D.L., Ressler, U., Dumontet, V., De Livera, A.M., Doronila, A., Baker, A.J.M. and Kolev, S.D. 2012. Elemental and metabolite profiling of nickel hyperaccumulators from New Caledonia. *Phytochemistry* 81: 80-89.
- Calvo, G., Mudd, G., Valero, A. and Valero, A. 2016. Decreasing ore grades in global metallic mining: a theoretical issue or a global reality?. *Resources* 5(4): 36, doi:10.3390/resources5040036.
- Chaney, R.L. and Baklanov, I.A. 2017. Chapter five-phytoremediation and phytomining: status and promise. *Advances in Botanical Research* 83: 189-221, doi:10.1016/bs.abr.2016.12.006.
- Damanik, C. 2019. Four People Killed in a Landslide at the Illegal Gold Mine Location in Kotabaru, <https://regional.kompas.com/read/2019/05/05/23013581/4-orang-tewas-tertimbun-longsor-di-lokasi-tambang-emas-ilegal-kotabaru>. Accessed January 28, 2019. (in Indonesian).
- Deng, T.H.B., Van der Ent, A., Tang, Y.T., Sterckemen, T., Echevarria, G., Morel, J.L. and Qiu, R. 2018. Nickel hyperaccumulation mechanisms: a review on the current state of knowledge. *Plant and Soil* 423(1-2): 1-11, doi:10.1007/s11104-017-3539-8.
- Esdaile, L.J. and Chalker, J.M. 2018. The mercury problem in artisanal and small-scale gold mining. *Chemistry European Journal* 24: 6905-6916, doi: 10.1002/chem.201704840.
- Fernando, E.S., Quimado, M.O., Trinidad, L.C. and Doronila, A.I. 2013 The potential use of indigenous nickel hyperaccumulators for small-scale mining in The

- Philippines. *Journal of Degraded and Mining Lands Management* 1(1): 21-26.
- Gamez, G., Dokken, K., Tiemann, K.J., Herrera, I., Yacaman, M.J., Renner, M.W., Furenlid, L.R. and Gardea-Torresdey, J.L. 1999. Spectroscopic Studies Of Gold(III) Binding To Alfalfa Biomass. *Proceedings of the 1999 Conference on Hazardous Waste Research*.
- Gardea-Torresdey, J.L., Rodriguez, E., Parsons, J.G., Peralta-Videa, J.R., Meitzner, G. and Cruz-Videa, G. 2005. Use of ICP and XAS to determine the enhancement of gold phytoextraction by *Chilopsis linearis* using thiocyanate as a complexing agent. *Analytical and Bioanalytical Chemistry* 382: 347-352, doi: 10.1007/s00216-004-2966-6.
- Gardea-Torresdey, J.L., Tiemann, K.J., Gamez, G., Dokken, K., Tehuacanero, S. and José-Yacamán, M. 1999. Gold nanoparticles obtained by bio-precipitation from gold (III) solutions. *Journal of Nanoparticle Research* 1: 397-404.
- Ghosh, M. and Singh, S.P. 2005. A review on phytoremediation of heavy metals and utilization of its by product. *Applied Ecology and Environmental Research* 3(1): 1-18.
- Girling, C.A. and Peterson, P.J. 1980. Gold in Plants, <https://link.springer.com/content/pdf/10.1007%2FBF03215461.pdf>.
- Goodman, P.S. and Griffith, T.L. 1991. A process approach to the implementation of new technology. *Journal of Engineering and Technology Management* 8(3-4): 261-265, doi: 10.1016/0923-4748(91)90014-I.
- Gove, B., Hutchinson, J.J., Young, S.D., Caragon, J. and McGrath, S.P. 2002. Uptake of metals by plants sharing a rhizosphere with the hyperaccumulator *Thlaspi caerulescens*. *International Journal of Phytoremediation* 4(4): 267-281.
- Gramss, G., Voigt, K-D. and Bregmann, H. 2004. Plant availability and leaching of (heavy) metals from ammonium-, calcium-, carbohydrate-, and citric acid-treated uranium-mine-dump soil. *Journal of Plant Nutrition and Soil Science* 167: 417-427.
- Grčman, H., Velikonja-Bolta, S., Vodnik, D. and Leštan, D. 2001. EDTA enhanced heavy metal phytoextraction: metal accumulation, leaching. *Plant and Soil* 235(1): 105-114, doi:10.1023/a:1011857303823.
- Handayanto, E., Muddarisna, N. and Krisnayanti, B.D. 2014. Induced phytoextraction of mercury and gold from cyanidation tailings of small-scale gold mining area of West Lombok, Indonesia. *Advances in Environmental Biology* 8(5): 1277-1284.
- Hentschel, T., Hruschka, F. and Priester, M. 2003. *Artisanal and Small-Scale Mining Challenges and Opportunities*. Russell Press Ltd, Nottingham, UK.
- Hunt, A.J., Anderson, C.W.N., Bruce, N., Garcia, A.M., Graedel, T.E., Hodson, M., Meech, J.A., Nassar, N.T., Parker, H.L., Rylott, E.L., Sotiriou, K., Zhang, Q. and Clark, J.H. 2014. Phytoextraction as a tool for green chemistry. *Green Processing and Synthesis* 3: 3-22, doi: 10.1515/gps-2013-0103.
- Jaszcak, E., Polkowska, Z., Narkowicz, S. and Namieśnik, J. 2017. Cyanides in the environment—analysis—problems and challenges. *Environmental Science and Pollution Research* 24:15929-15948.
- Kavanagh, L., Keohane, J., Cabellos, G.C., Lloyd, A. and Cleary, J. 2018. Induced plant accumulation of lithium, *Geosciences* 8: 56, doi:10.3390/geosciences8020056.
- Keeling, S.M., Stewart, R.B., Anderson, C.W.N. and Robinson, B.H. 2003. Nickel and cobalt phytoextraction by the hyperaccumulator *Barkheya coddii*: implications for polymetallic phytomining and phytoremediation. *International Journal of Phytoremediation* 5: 235-244.
- Kidd, P.S., Bani, A., Benizri, E., Gonnelli, C., Hazotte, C., Kissler, J., Konstantinou, M., Kuppens, T., Kyrkas, D., Laubie, B., Malina, R., Morel, J.L., Olcay, Pardo, T., Pons, M.N., Fernández, A.P., Puschenreiter, M., Quintela-Sabaris, C., Ridard, C., Rodríguez-Garrido, B., Rosenkranz, T., Rozp, P., Saad, R., Selvi, F., Simonnot, M-O., Tognacchini, A., Turnau, K., Wazny, R., Witters, N. and Echevarria, G. 2018. Developing sustainable agromining systems in agricultural ultramafic soils for nickel recovery. *Frontier in Environmental Science* 6(44), doi: 10.3389/fenvs.2018.00044.
- Kivinen, S. 2017. Sustainable post-mining land use: are closed metal mines abandoned or re-used space?, *Sustainability* 9: 1705, doi:10.3390/su9101705.
- Krisnayanti, B.D., Anderson, C.W.N., Sukartono, S., Afandi, Y., Suheri, H. and Ekawanti, A. 2016. Phytomining for artisanal gold mine tailings management. *Minerals* 6:84, doi:10.3390/min6030084.
- Krisnayanti, B.D. 2018. ASGM status in West Nusa Tenggara Province, Indonesia. *Journal of Degraded and Mining Lands Management* 5(2): 1077-1084, doi: 10.15243/jdmlm.2018.052.1077.
- Krisnayanti, B.D., Anderson, C.W.N., Utomo, W.H., Feng, X., Handayanto, E., Muddarisna, N., Ikram, H. and Khususiah, K. 2012. Assessment of environmental mercury discharge at a four-year-old artisanal gold mining area on Lombok Island, Indonesia. *Journal of Environmental Monitoring* 14: 2598-2607, doi: 10.1039/c2em30515a.
- Krisnayanti, B.D., Vasurra, I., Asmara, M.D., Ekawanti, A. and Suheri, H. 2016. Analysis of artisanal small-scale gold mining sector in West Sumbawa Regency, Indonesia. *Journal of Health and Pollution* 6(12): 26-33, doi: 10.5696/2156-9614-6.12.26.
- Krisnayanti, D.B. and Anderson, W.C. 2014. Gold phytomining: a new idea for environmental sustainability in Indonesia. *Indonesian Journal on Geoscience* 1(1): 1-7.
- Kristianto, Y., Ajmal, M., Tenkorang, R.A. and Hussain, M. 2012. A study of technology adoption in manufacturing firms, *Journal of Manufacturing Technology Management* 23(2): 198-211, doi:10.1108/17410381211202197.
- Kumah, A. 2004. Sustainability and gold mining in the developing world. *Journal of Cleaner Production* 14 (3-4): 315-323, doi: 10.1016/j.jclepro.2004.08.007.
- Lamb, A.E., Anderson, C.W.N. and Haverkamp R.G. 2001. The extraction of gold from plants and its application to phytomining. *Chemistry New Zealand* 9: 31-33.
- Lamb, A.E., Anderson, C.W.N. and Haverkamp, R.G. 2001. The induced accumulation of gold in the plants *Brassica juncea*, *Barkheya coddii* and Chicory. *Chemistry New Zealand* 34-36.
- Leeuwen, T. 2014. A Brief History of Mineral Exploration and Mining in Sumatra. *Proceedings of Sundaland Resources 2014 MGEI Annual Convention*.
- Leitanmaier, B. and Küpper, H. 2013. Compartmentation and complexation of metals in hyperaccumulator plants. *Frontiers in Plant Science* Volume 4, Article 374, 1-13, doi: 10.3389/fpls.2013.00374.

- Levinson, Z. and Dimitrakopoulos, R. 2019. Simultaneous stochastic optimisation of an open-pit gold mining complex with waste management. *International Journal of Mining, Reclamation and Environment* 34(6): 1–15. doi:10.1080/17480930.2019.1621441.
- Losfeld, G., Escande, V., Jaffrè, T., L'Huillier, L. and Grison, C. 2012. The chemical exploitation of nickel phytoextraction: An environment, ecologic and economic opportunity for New Caledonia. *Chemosphere* 89: 907-910.
- Lu, L., Tian, S., Yang, X., Li, T. and He, Z. 2009. Cadmium uptake and xylem loading are active processes in the hyperaccumulator *Sedum alfredii*. *Journal of Plant Physiology* 166: 579-587.
- Macdonald, F.K.F., Lund, M., Blanchette, M. and McCullough, C. 2014. Regulation of Artisanal Small Scale Gold Mining (ASGM) in Ghana and Indonesia as Currently Implemented Fails to Adequately Protect Aquatic Ecosystems, An Interdisciplinary Response to Mine Water Challenges - Sui, Sun & Wang (eds).
- MacDonald, T.N. 2015. Potassium cyanide and the effect on the rate of decomposition of mice in grave-soil. *Forensic Research & Criminology International Journal* 1(2): 57-64, doi: 10.15406/frcij.2015.01.00010.
- Macháček, J. 2019. Typology of environmental impacts of artisanal and small-scale mining in African Great Lakes Region. *Sustainability* 11: 3027, doi:10.3390/su11113027.
- Male, Y.T., Reichelt-Brushett, A.J.R., Pocock, M. and Nanlohy, A. 2013. Recent mercury contamination from artisanal gold mining on Buru Island, Indonesia – Potential future risks to environmental health and food safety. *Marine Pollution Bulletin* 77: 428-433.
- Manus, M. 2005: *Kalimantan Indonesia: Macroeconomic Policy Change and the Environmental Impacts of the Mining Sector*. Macroeconomic Program Office, WWF.
- McDonald, F.K.F., Lund, M., Blanchette, M. and McCullough, C. 2014. Regulation of Artisanal Small Scale Gold Mining (ASGM) in Ghana and Indonesia as Currently Implemented Fails to Adequately Protect Aquatic Ecosystems, An Interdisciplinary Response to Mine Water Challenges - Sui, Sun & Wang (eds), China University of Mining and Technology Press, Xuzhou.
- McGrew, L. 2016. Artisanal and Small Scale Gold Mining: A Sector of Problems and A Sector of Promise, <https://www.asiapacific.ca/blog/artisanal-and-small-scale-gold-mining-sector-problems-and>, Accessed January 28, 2020.
- Miall, H., Ramsbotham, O. and Woodhouse, T. 2000. *Peaceful Resolution of Contemporary Conflicts: Resolving, Preventing, Managing and Changing Conflicts of Political, Social, Religious and Racial Origin*. Rajagrafindo Persada. Jakarta (in Indonesian).
- Mohanty, M. 2016. Post-harvest management of phytoremediation technology. *Journal of Environmental and Analytical Toxicology* 6: 5, doi: 10.4172/2161-0525.1000398.
- Msuya, F.A., Brooks, R.R. and Anderson, C.W.N. 2000. Chemically-induced uptake of gold by root crops: its significance for phytomining. *Gold Bulletin* 33(4): 134-137, doi: 10.1007/BF03215491
- Muddarisna, N. and Krisnayanti, B.D. 2015. Selection of mercury accumulator plants for gold mine tailing contaminated soils. *Journal of Degraded and Mining Lands Management* 2(3): 341-346. doi: 10.15243/jdmlm.2015.023.341.
- Muddarisna, N., Krisnayanti, B.D., Utami, S.R. and Handayanto, E. 2013. The potential of wild plants for phytoremediation of soil contaminated with mercury of gold cyanidation tailings. *IOSR Journal of Environmental Science, Toxicology and Food Technology* 4(1): 15-19.
- Mutsvanga, T., Mapira, J. and Ngaza, N. 2018. Gold ore waste management challenges at Renco mine, Zimbabwe. *European Journal of Social Sciences Studies* 3(3): 15-34, doi: 10.5281/zenodo.1419529.
- Nkrumah, P.N., Chaney, R.L. and Morel, J.L. 2018. Agronomy of 'Metal Crops' Used in Agromining. In: van der Ent, A. (ed). *Farming Agromining: Farming for Metals; Extracting Unconventional Resources Using Plants*. Springer International Publishing.
- Northey, S., Mohr, S., Mudd, G.M., Weng, Z. and Giurco, D. 2014. Modelling future copper ore grade decline based on a detailed assessment of copper resources and mining. *Resources, Conservation and Recycling* 83:190–201.
- Obiri, S., Mattah, P.A.D., Mattah, M.M., Armah, F.A., Osae, S., Adu-kumi, S. and Yeboah, P.O. 2016. Assessing the environmental and socio-economic impacts of artisanal gold mining on the livelihoods of communities in the Tarkwa Nsuaem Municipality in Ghana. *International Journal of Environmental Research and Public Health* 13: 160, doi:10.3390/ijerph13020160.
- Orłowska, E., Przybyłowicz, W., Orłowski, D., Mongwaketsi, N.P., Turnau, K. and Mesjasz-Przybyłowicz, J. 2013. Mycorrhizal colonization affects the elemental distribution in roots of Ni-hyperaccumulator *Berkheya coddii* Roessler. *Environmental Pollution* 175: 100-109.
- Owusu, O., Bansah, K.J. and Mensah, A.K. 2019. "Small in size, but big in impact": Socio-environmental reforms for sustainable artisanal and small-scale mining, *Journal of Sustainable Mining* 18(1): 38-44, doi: 10.1016/j.jsm.2019.02.001.
- Performance Report of the Directorate General of Mineral and Coal. 2016. Directorate General of Mineral and Coal, Ministry of Energy and Mineral Resources of the Republic of Indonesia Indonesia, [https://www.minerba.esdm.go.id/library/publish/LAKI N%20MINERBA%202016.pdf](https://www.minerba.esdm.go.id/library/publish/LAKI%20MINERBA%202016.pdf) (in Indonesian).
- Piccinin, R.C.R., Ebbs, S.D., Reichman, S.M., Kolev, S.D., Woodrow, I.E. and Baker, A.J.M. 2007. A screen of some native Australian flora and exotic agricultural species for their potential application in cyanide-induced phytoextraction of gold. *Minerals Engineering* 20: 1327-1330.
- Plasmanto, G. 2019. Illegal Gold Mine in Jambi Landslides, 1 Killed and 5 Miners Still Buried. <https://www.liputan6.com/regional/read/4139996/tambang-emas-ilegal-di-jambi-longsor-1-tewas-dan-5-penambang-masih-tertimbun>, Accessed January 28, 2019 (in Indonesian).
- Prasad, M.N.V. and Freitas, H.M.O. 2003. Metal hyperaccumulation in plants - Biodiversity prospecting for phytoremediation technology. *Electronic Journal of Biotechnology* 6(3): 110-146.
- Prasetya, B., Krisnayanti, B.D., Utomo, W.H. and Anderson, C.W.N. 2010. Rehabilitation of artisanal mining gold land in West Lombok, Indonesia: 2. Arbuscular mycorrhiza status of tailings and surrounding soils. *Journal of Agricultural Science* 2(2): 202-2019,, doi:10.5539/jas.v2n2p202.

- Puluhulawa, F. and Harun, A.A., 2019. Policy formalization of Artisanal and Small-Scale Gold Mining (ASGM) post-ratification of Minamata Convention for Sustainability (a case study of ASGM Gorontalo). *E3S Web of Conferences* 125, 0, doi: 10.1051/e3sconf/20191250.
- Rahim, S. 2017. Conflict in spatial use due to unlicensed gold mining (PETI) in limited production forest areas. *Jurnal GeoEco* 3(1): 17-25 (in Indonesian).
- Ramadhan, D.T., Budiman, A. and Solearno, S.W. 2014. Conflict resolution between local communities and mining companies (case study: Naga Juang District, Mandailing Natal Regency, North Sumatra Province). *Jurnal Ilmu Lingkungan* 12(2): 92-104 (in Indonesian).
- Rascio, N. and Navari-Izzo, F. 2011. Heavy metal hyperaccumulating plants: How and why do they do it? And what makes them so interesting?, *Plant Science* 180:169–181.
- Redi, A. 2016. The dilemma of law enforcement of mineral and coal mining without permits in small scale mining *Jurnal Rechts Vinding* 5(3): 399-420 (in Indonesian).
- Reeves, R.D., Baker, A.J.M., Jaffré, T., Erskine, P.D., Echevarria, G. and Van der Ent, A. 2017. A global database for plants that hyperaccumulate metal and metalloid trace elements. *New Phytologist* 218: 407-411, doi: 10.1111/nph.14907.
- Reeves, R.D. and Adigüdzél, N. 2008. The nickel hyperaccumulating plants of the serpentines of Turkey and adjacent areas: a review with new data. *Turkish Journal of Biology* 32: 143-153.
- Reith, F., Brugger, J., Zammit, C.M., Nies, D.H. and Southam, G. 2013. Geobiological cycling of gold: from fundamental process understanding to exploration solutions. *Minerals* 3: 367-394, doi: 10.3390/min3040367.
- Rintelen, K., Arida, E. and Hauser, C. 2017. A review of biodiversity-related issues and challenges in megadiverse Indonesia and other Southeast Asian countries. *Research Ideas and Outcomes* 3: e20860.
- Rodriguez-Lopez, M., Wilson-Corral, V., Anderson, C. and Lopez-Perez, J. 2009. Chemically assisted gold phytoextraction in Sorghum halepense. In: *The 5th International Conference on Gold Science, Technology and Its Applications*. World Gold Council, Heidelberg, p. 353.
- Sastrapradja, S.D. 2005. Conservation of trees and plants at the village level in Indonesia. *Biodiversity* 6(1): 13-16, doi: 10.1080/14888386.2005.9712754.
- Schrama, F.N.H., Beunder, E.M., Berg, B.V. and Boom, R. 2017. Sulphur removal in ironmaking and oxygen steelmaking. *Ironmaking & Steelmaking* 44(5): 333-343, doi: 10.1080/03019233.2017.1303914.
- Semrau, K.T. 1971. Sulfur oxides control and metallurgical technology. *Journal of Metals* 23(3): 41-47, doi:10.1007/bf03355689.
- Shacklette, H.T., Lakin, H.W., Hubert, A.E. and Curtin, G.C. 1970. Absorption of gold by plants. *U.S. Geological Survey Bulletin* 1314-B 1–23.
- Sheoran, V., Sheoran, A.S. and Poonia, P. 2009. Phytomining: a review. *Mineral Engineering* 22(12): 1007-1019, doi: 10.1016/j.mineng.2009.04.001.
- Sheoran, V., Sheoran, A.S. and Poonia, P. 2013. Phytomining of gold: A review. *Journal of Geochemical Exploration* 128: 42–50, doi: 10.1016/j.gexplo.2013.01.008.
- Simonnot, M.O., Laubie, B., Zhang, X., Houzelot, V., Ferrari, F., Rodrigues, J., Pons, M.N., Bani, A.M. Echevarria, G. and Morel, J.L. 2016. Agromining: Producing Ni Salts from The Biomass of Hyperaccumulator Plants, *International Mineral Processing Congress Proceedings, IMPC*.
- Sobczyk, M.K., Smith, J.A.C., Pollard, A.J. and Filatov, D.A. 2017. Evolution of nickel hyperaccumulation and serpentine adaptation in the *Alyssum serpyllifolium* species complex. *Heredity* 118: 31–41.
- Soelistijo, U.W., Anjani, P.L., Pratama, H.I., La Pili, H. and Herdayanti, M.K. 2015. Trend of mineral commodity price and its impact on the Indonesian economy 1990-2025. *Earth Sciences* 4(4): 129-145.
- Spiegel, S.J., Agrawal, S., Mikha, D., Vitamerry, K., Le Billon, P., Veiga, M., Konolius, K. and Paul, B. 2018. Phasing out mercury? Ecological economics and Indonesia's small-scale gold mining sector. *Ecological Economics* 144: 1-11, doi: 10.1016/j.ecolecon.2017.07.025.
- Swaroop, G., Bulbule, K.A., Parthasarathy, P., Shivakumar, Y., Muniswamy, R., Annamati, R. and Priyanka, D. 2013. Application of gold ore tailings (GOT) as a source of micronutrients for the growth of plants. *International Journal of Scientific World* 1(3): 68-78.
- Syafrizal, S., Rivai, T.A., Yonezu, K., Kusumanto, D., Watanabe, K. and Hede, A.N.H. 2017. Characteristics of a low-sulfidation epithermal deposit in the river reef zone and the Watuputih hill, the Poboya gold prospect, Central Sulawesi, Indonesia: host rocks and hydrothermal alteration. *Minerals* 7: 124, doi:10.3390/min7070124.
- Taye-bi-khorami, M., Edraki, M., Corder, G. and Golev, A. 2019. Re-thinking mining waste through an integrative approach led by circular economy aspirations. *Minerals* 9: 286, doi:10.3390/min9050286.
- Thomsen, M.B. 2017. High Sulphidation Gold Deposits A Retrospective Summary, <https://www.researchgate.net/publication/314183136>.
- Topstad, M. and Karlsen, B. 2015. Impacts of the new Indonesian mining regulations. MSc thesis, at the University of Agder, Norway.
- Trimiska, L., Wiryono, W. and Suhartoyo, H. 2018. Study of gold mining without permits (PETI) in Lebong Utara District, Lebong Regency. *Naturalis* 7(1): 1-8 (in Indonesian).
- UNEP Final Report. 2014. [https://wedocs.unep.org/bitstream/handle/20.500.11822/11708/FinalReportNarrative\\_June2014.pdf?sequence=1&isAllowed=y](https://wedocs.unep.org/bitstream/handle/20.500.11822/11708/FinalReportNarrative_June2014.pdf?sequence=1&isAllowed=y).
- Van der Eng, P. 2014. Mining and Indonesia's Economy: Institutions and Value Adding. 1870-2010, *PRIMCED Discussion Paper Series* No. 57.
- Van der Ent, A., Baker, A.J.M., Balgooy, M.M.J. and Tjoa, A. 2013. Ultramafic nickel laterites in Indonesia (Sulawesi, Halmahera): mining, nickel hyperaccumulators and opportunities for phytomining. *Journal of Geochemical Exploration* 128: 72–79.
- Van der Ent, A.V., Baker, A.J.M., Reeves, R.D., Chaney, R.L., Anderson, C.W.N., Meech, J.A., Erskine, P.D., Simonnot, M-O., Vaughan, J., Morel, J.L., Echevarria, G., Fogliani, B., Rongliang, Q. and Mulligan, D.R. 2015. Agromining: farming for metals in the future?. *Environmental Science and Technology* 49: 4773-4780, doi: 10.1021/es506031u.

- Veiga, M.M., Angeloci-Santos, G. and Meech, J.A. 2014. Review of barriers to reduce mercury use in artisanal gold mining. *The Extractive Industries and Society* 1(2): 340-350, doi:10.1016/j.exis.2014.03.004.
- Verbruggen, N., Hermans, C. and Schat, H. 2009. Molecular mechanisms of metal hyperaccumulation in plants. *New Phytologist* 181: 759-776.
- Wahyudi, E. and Slamet. 2015. The Social Impact of Gold Mining Without Permits (PETI) on the Sustainability of Rice Farming in Merangin District, Jambi Province, Proceedings of the National Seminar on Site-Specific Agroinnovations for Food Security in the Era of the ASEAN Economic Community. [http://lampung.litbang.pertanian.go.id/ind/images/stories/publikasi/prosiding\\_1\\_2017/38.erwanwahyudi.pdf](http://lampung.litbang.pertanian.go.id/ind/images/stories/publikasi/prosiding_1_2017/38.erwanwahyudi.pdf) (in Indonesian).
- Wan, X., Lei, M., Chen, T., Yang, J., Liu, H. and Chen, Y. 2015. Role of transpiration in arsenic accumulation of hyperaccumulator *Pteris vittata* L. *Environmental Science and Pollution Research* 22: 16631-16639.
- Wilson-Corral, V., Anderson, C.W.N. and Rodriguez-Lopez, M. 2012. Gold phytomining. A review of the relevance of this technology to mineral extraction in the 21st century. *Journal of Environmental Management* 111: 249-257, doi:10.1016/j.jenvman.2012.07.037.
- Wilson-Corral, V., Rodriguez-Lopez, M., Lopez-Perez, J., Arenas-vargas, M. and Anderson, C. 2013. Gold phytomining in arid and semiarid soils. *Proceeding of 19<sup>th</sup> World Congress of Soil Science, Soil Solutions for a Changing World*.
- Wisuda, A. 2020. Illegal Gold Mining and Damage in the Upstream Causes Floods and Landslides in Bogor Regency. <https://www.mongabay.co.id/2020/01/20/tambang-emas-ilegal-dan-alih-fungsi-lahan-diduga-jadi-penyebab-banjir-dan-longsor-di-kabupaten-bogor/>, accessed January, 28 2020 (in Indonesian).
- Wood, B.W., Chaney, R.L. and Crawford, M. 2006. Correcting micronutrient deficiency using metal hyperaccumulators: *Alyssum* biomass as a natural product for nickel deficiency correction. *HortScience* 41: 1231e1234.